PRESTO GEOSYSTEMS

GEOTERRA®

SPECIFICATION SUMMARY

Table 1 GEOTERRA® Unit

Item	Specifications & Details
Material	Up to 100% Recycled Polyethylene*
Color	Ranges from dark shades of gray to black
Chemical Resistance	Superior
Carbon Black for Ultraviolet Light Stabilization	1.5% - 2.0%
Unit Minimum Crush Strength @ 21°C (70°F)	2,900 kPa (420 psi)
Material Flexural Modulus at 23°C (73°F)	240,000 kPa (35,000 psi)
Nominal Dimensions (width x length)	0.48 m x 0.96 m (18.84 in x 37.80 in)
Nominal Unit Depth	50 mm (2 in)
Nominal Coverage Area	0.46 m² (4.95 ft²)
Cells per Unit	72
Cell Size	79 mm x 81 mm (3.1 in x 3.2 in)
Top Open Area per unit	87%
Bottom Open Area per unit	41%
Nominal Weight per Unit	4.5 kg (9.9 lb)
Units per Pallet	50

NOTE: Dimensions and weight are subject to manufacturing tolerances and are influenced by recycled component characteristics.

PRESTO GEOSYSTEMS
670 N PERKINS STREET, APPLETON, WISCONSIN, USA 54914
Ph: 920-738-1328 or 800-548-3424 ■ Fax: 920-738-1222
e-mail: INFO@PRESTOGEO.COM WWW.PRESTOGEO.COM
APRIL 1, 2015