


Alternative Permeable Surfacing




Material Mixing Guide

Available in 8 colors



Gray



Green



Cypress



Black




Brown



Tan



Redwood



Blue

Porous Pave XL

Base Mixing Ratio

- 1 - 50# bag of rubber chips
- 1 - 50# bag of aggregate
- 5 Quarts of B5HN hard binder

Base Coverage Guide

Thickness	Coverage
1"	24 sq ft.
1.5"	16 sq ft.
2"	12 sq ft.

Typical Batch Mixture

For typical batches **double** base mixture in an 8 cubic ft or larger mixer.

Porous Pave XLS

Base Mixing Ratio

- 1 - 50# bag of rubber chips
- 3 1/3 Quarts of B5SN soft binder

Base Coverage Guide

Thickness	Coverage
1"	16 sq ft.
2"	8 sq ft.

Typical Batch Mixture

For typical batches **triple** base mixture in an 8 cubic ft or larger mixer.

Important Mixing Tips

- Mix in mortar mixer 45-60 seconds or until material is evenly coated with binder, over-mixing may change the color of the material.
- Oil mixer frequently with vegetable oil in between batches, this will keep the material from sticking to the mixer and aid in clean up.